

## Technical Data Sheet

<b>Name:</b>	Red Clay.
<b>INCI Name:</b>	Kaolin.
<b>CAS number:</b>	N/A.
<b>Scientific Name:</b>	<i>Kaolin.</i>
<b>Type of Product:</b>	Powder.
<b>Origin:</b>	Brazil.
<b>Description:</b>	Product obtained by through collection on the rivers and sundried. Without preservatives.
<b>Ingredients:</b>	Red Clay.
<b>Applications:</b>	Cosmetics, phytotherapy, pharmaceuticalonly, not suited for human consumption.
<b>Packing:</b>	Drums of 180 kg and 50 kg, pails of 20 kg and 5 kg and 1 kg.
<b>Shelf Life and Storage Conditions:</b>	24 months, if maintained in the original closed package at a temperature at least 15°C. Keep product away from light, moisture and heat.
<b>Transportation:</b>	In clean vehicles, protected from dust, moisture and material that can offer contaminations risk.

### ORGANOLEPTICAL CHARACTERISTICS\*

Analysis	Specification
Color	Light Red to Dark Red
Appearance	Fine Powder
Odor	Characteristic

\* Natural raw materials of vegetable origin can suffer color and odor changes between different batches of product.

### PHYSICAL & CHEMICAL CHARACTERISTICS

Analysis	Method	Specification
Granulometric distribution in suspension (average diameter in $\mu\text{m}$ )	Sifting	Max. 15
SiO <sub>2</sub> (%)	XRF	66 - 69
Fe <sub>2</sub> O <sub>2</sub> (%)	XRF	1.5 - 2.5
CaO (%)	XRF	< 0.06
P <sub>2</sub> O <sub>5</sub> (%)	XRF	< 0.3
Al <sub>2</sub> O <sub>3</sub> (%)	XRF	17 - 20
Na <sub>2</sub> O (%)	XRF	< 0.3
TiO <sub>2</sub> (%)	XRF	< 1.3
MgO (%)	XRF	0.15 - 0.40
K <sub>2</sub> O (%)	XRF	< 0.20
Pb ( $\mu\text{g/g}$ )	AAS	< 20
As ( $\mu\text{g/g}$ )	AAS	< 10
Hg ( $\mu\text{g/g}$ )	AAS	< 1
Sb ( $\mu\text{g/g}$ )	AAS	< 10
Cd ( $\mu\text{g/g}$ )	AAS	< 5

\* Reference Values Only

The information contained in this publication represents the best of our knowledge. Users should, however, conduct their own tests to determine the suitability of our products for their own specific purposes. Statements contained herein should not be considered as a warrant of any kind, expressed or implied, and no liability is accepted for the infringement of any patents.